

Gulf Eskimo

High Performance Naphthenic Refrigeration Compressor oil

Product Description

Gulf Eskimo series are high performance naphthenic refrigeration compressor oils specially designed to meet the stringent requirements of major refrigeration compressor manufacturers. These oils are formulated with severely hydro treated naphthenic base oils to provide excellent protection against oxidation degradation, rust & corrosion and foaming & entrained air. These oils are specifically designed for refrigeration systems using non-hydroflurocarbon refrigerants such as R-11, R-12, R-13B1 R-22, R-113, R-500, R-501, R-502, R-717 (Ammonia - NH3), etc. These oils exceed the performance requirements of DIN 51503 KAA, KC and KE and ISO 6743-3:2003 L-DRA, L-DRE and L-DRG.

Features & Benefits

- Good thermo-oxidative stability controls deposits in evaporator tubes, improves heat transfer and improves oil life resulting in improved equipment reliability, availability and efficiency.
- Free from additives and pour point depressants as these have been known to impair the performance of some refrigeration systems
- Low pour point and floc point ensures smooth operation at low operating temperatures
- Low ash and carbon forming tendency ensures improved valve performance and reduced potential for fires and explosions in the discharge systems.
- Good wear and rust protection results in reduced maintenance costs and longer equipment life.
- Compatible with materials used in the entire refrigeration system.

Applications

- Large Industrial reciprocating and rotary refrigeration compressors.
- Suitable for use with most non-hydroflourocarbon refrigerant gases like R-11, R-12, R-13B1 R-22, R-113, R-500, R-501, R-502, R-717 (Ammonia NH3), CO2, etc compressors of Carrier, Copeland, Kelvinator, Sabroe, Tecumseh make among others where such quality oils are recommended.
- Marine refrigeration applications like food freezing and cold storage plants
- Also used in circulating oil systems, plain and rolling element bearings, etc
- NOTE: These oils are NOT recommended for use with HFC refrigerants such as R-134a.

Specifications, Approvals & Typical Properties

| epoomoanone, Approvate a Typican | p | | | | |
|--|-------------|--------|----------------|---------|--|
| ISO Viscosity grades | | 32 | 46 | 68 | |
| Specification | | | | | |
| DIN 51503 KAA, KC and KE | | Х | Х | Х | |
| ISO 6743-3:2003 L-DRA, L-DRE and L-DRG | | Х | Х | Х | |
| Typical Properties | | | | | |
| Test Parameters | ASTM Method | Ту | Typical Values | | |
| Viscosity @ 40 °C, cSt | D 445 | 32.1 | 45.9 | 68.9 | |
| Flash Point, °C | D 92 | 184 | 188 | 206 | |
| Pour Point, °C | D 97 | -42 | -39 | -36 | |
| Density @ 15°C, Kg/l | D 1298 | 0.915 | 0.921 | 0.921 | |
| Conradson Carbon Residue (CCR), %m | D 189 | < 0.01 | < 0.01 | < 0.01 | |
| Rust Test | D 665 A/B | Pass | Pass | Pass | |
| Copper Corrosion, 1hr @ 100°C | D 130 | 1a | 1a | 1a | |
| Total Acid Number, mg KOH/g | D 974 | 0.01 | 0.01 | 0.01 | |
| Flocculation Point, R-12 | DIN 51351 | -40 | -36 | -31 | |
| Saponification No. mg KOH/gm | D 94 | 0.05 | 0.05 | 0.05 | |
| | | | | A I OOO | |

April 2022

Properties mentioned are typical only and minor variations, which do not affect product performance, are expected to arise in normal manufacturing processes. Please follow equipment manufacturer's recommendations for performance level and viscosity grade. The Safety Data Sheet for this product is available from your nearest Gulf Distributor. Please consult our local representative if any further information is required.